



Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 MyDay[®] MiSight[®] 1 day	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	---	---	Treatment zones offer +2.00D of myopic defocus	Dual-focus	ActivControl [®] Technology	Daily wear; Recommendation to wear the lenses for a minimum of 10 hours per day for at least 6 days per week [‡] ; 1 day replacement	8.4	14.2	0.080	Aquaform [®] Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MiSight[®] 1 day	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	---	---	Treatment zones offer +2.00D of myopic defocus	Dual-focus	ActivControl [®] Technology	Daily wear; Recommendation to wear the lenses for a minimum of 10 hours per day for at least 6 days per week [‡] ; 1 day replacement	8.7	14.2	0.090	PC Technology [®] (phosphoryl choline)	omafilcon A	60	28	0.3	No	Yes	2

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) × 10⁻⁹ [(cm/sec) × (ml O₂) / (ml × mmHg)]





[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 MyDay[®]	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	—	—	—	Asphere	Aberration Neutralizing System™	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform [®] Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay[®] toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	—	Toric	Optimized Toric Lens Geometry™	Daily wear; 1 day replacement	8.6	14.5	0.100	Aquaform [®] Technology	stenfilcon A	54	80	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay[®] multifocal	-12.00 to -10.50 (0.50 steps) -10.00 to +8.00 (0.25 steps)	—	—	Low (+0.75 to +1.25 spectacle add) Med (+1.50 to +1.75 spectacle add) High (+2.00 to +2.50 spectacle add)	Multifocal	Binocular Progressive System™	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform [®] Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay Energys[®] (coming 2026)	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	—	—	—	Asphere	ComfortBoost [®]	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform [®] Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]





‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

§ Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 clariti® 1 day sphere	-10.00 to -6.50 (0.50 steps) -6.00 to -0.50 (0.25 steps) +0.50 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— — —	— — —	— — —	Asphere	— — —	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
 clariti® 1 day toric	-9.00 to -6.50 (0.50 steps)	-0.75 -1.25 -1.75	10, 20, 60, 70, 80, 90, 100, 110, 120, 160, 170, 180	— — —	Toric	Smooth-gradient ballast toric design	Daily wear; 1 day replacement	8.6	14.3	0.105	WetLoc® Technology	somofilcon A	56	57	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
	-6.00DS to Plano (0.25 steps)	-2.25	10, 20, 70, 80, 90, 100, 110, 160, 170, 180	— — —														
	+0.25 to +4.00 (0.25 steps)	-0.75 -1.25 -1.75	10 to 180 (10 steps)															
 clariti® 1 day Multifocal (3 add) (available from March 2026)	-12.00 to -10.50 (0.50 steps) -10.00 to +8.00 (0.25 steps)	— — —	— — —	Low (+0.75 to +1.25 spectacle add) Med (+1.50 to +1.75 spectacle add) High (+2.00 to +2.50 spectacle add)	Multifocal	Binocular Progressive System™	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
 clariti® 1 day multifocal	-6.00 to +5.00 (0.25 steps)	— — —	— — —	Low; Up to +1.25 High; +1.50 to +2.25	Multifocal	— — —	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]




‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

§ Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS)*	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t†	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Live® daily disposable	10.00 to -6.50 (0.50 steps) -6.00 to -0.50 (0.25 steps) +0.50 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	---	---	---	Asphere	---	Daily wear; 1 day replacement	8.6	14	0.070	AquaGen® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
 Proclear® 1 day	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	---	---	---	Asphere	Aberration Neutralizing System™	Daily wear; 1 day replacement	8.7	14.2	0.090	PC Technology® (phosphoryl choline)	omafilcon A	60	28	0.3	No	Yes	2
 Proclear® 1 day multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to +6.00 (0.25 steps)	---	---	Single power profile +1.50D (Could fit adds up to +2.50)	Multifocal	---	Daily wear; 1 day replacement	8.7	14.2	0.090	PC Technology® (phosphoryl choline)	omafilcon A	60	28	0.3	No	Yes	2

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]



‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

§ Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS)*	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t†	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Biomedics® 1 day Extra	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	---	---	---	Spherical optic (sphere)	---	Daily wear; 1 day replacement	8.6	14.2	0.075	---	ocufilcon D	55	26	0.5	No	Yes	4
	+6.00 to +0.25 (0.25 steps) NO PLANO	---	---	---				8.8										
 Biomedics® 1 day Extra toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps)	-0.75, -1.25, -1.75	10 to 180 (in 10 steps)	---	Toric	Optimized Toric Lens Geometry™	Daily wear; 1 day replacement	8.7	14.5	0.109	---	ocufilcon D	55	18	0.5	No	Yes	4

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]





‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Biomedics®, clariti®, CooperVision®, live®, MyDay®, MyDay Energys®, MiSight® and Proclear® are registered trademarks of The Cooper Companies, Inc. and its subsidiaries.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS)*	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t†	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Biofinity®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	---	---	---	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement Extended wear; 7 days/6 nights; 30 day replacement	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity® XR	-20.00 to -12.50 (0.50 steps) +8.50 to +15.00 (0.50 steps)	---	---	---	Asphere	Aberration Neutralizing System™	As for Biofinity sphere	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity Energys®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	---	---	---	Asphere	Digital Zone Optics®	As for Biofinity sphere	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity® toric	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	---	Toric	Optimized Toric Lens Geometry™	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)

* Plano lens availability for sphere product can vary by market or customer.




† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)] / (ml x mmHg)]

‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS)*	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t†	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Biofinity® XR Toric	-20.00 to -10.50 (0.50 steps) +8.50 to +20.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	5 to 180 (5 steps)	—	Toric	Optimized Toric Lens Geometry™	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)
	-20.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +20.00 (0.50 steps)	-2.75 -3.25 -3.75 -4.25 -4.75 -5.25 -5.75																
 Biofinity® multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	—	—	+1.00 +1.50 +2.00 +2.50	Multifocal D lens N Lens	Balanced Progressive® Technology	As for Biofinity sphere	8.6	14	0.090 to 0.110 (add dependant)	Aquaform® Technology	comfilcon A	48	142 (-3.00, N lens, +1.00 Add)	0.6	No	Yes	5C (SiHy)
 Biofinity® toric multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +10.00 (0.50 steps)	-0.75 to -5.75 (0.50 steps)	5 to 180 (5 steps)	+1.00 +1.50 +2.00 +2.50	Toric Multifocal Aspheric FS-D Lens N Lens	Optimized Toric Lens Geometry™ Balanced Progressive® Technology	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]





‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Frequently Replaced Products

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Avaira Vitality®	-12.00 to -6.50 (0.50 steps)	---	---	---	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement	8.4	14.2	0.080	---	fanfilcon A	55	112	0.5	93% UVA & 100% UVB; Class 1	Yes	5B (SiHy)
	-6.00 to -0.25 (0.25 steps)																	
	+0.25 to +6.00 (0.25 steps)																	
	+6.50 to +8.00 (0.50 steps)																	
NO PLANO																		
 Avaira Vitality® toric	-10.00 to -6.50D (0.50D steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	---	Toric	Optimized Toric Lens Geometry™	Daily wear; 30 days replacement	8.5	14.5	0.100	---	fanfilcon A	55	90	0.5	93% UVA & 100% UVB; Class 1	Yes	5B (SiHy)
	-6.00 to -plano (0.25D steps)																	
	+0.25 to +6.00D (0.25D steps)																	
	+6.50 to +8.00D (0.50D steps)																	
 Proclear®	-10.00 to -6.50 (0.50 steps)	---	---	---	Asphere	---	Daily wear; 30 days replacement	8.2	14.2	0.075	PC Technology® (phosphoryl choline)	omafilcon B	62	36	0.4	No	Yes	2
	-6.00 to -0.25 (0.25 steps)																	
	+0.50 to +6.00 (0.25 steps)							8.6										
	+6.50 to +20.00 (0.50 steps)																	
NO PLANO																		
 Proclear® toric	-8.00 to -7.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	---	Toric	---	Daily wear; 30 days replacement	8.4 (MTO)	14.4	0.138	PC Technology® (phosphoryl choline)	omafilcon B	62	16 (MTO)	0.4	No	Yes	2
	-6.50 to Plano (0.25 steps)							8.8 (MTO or moulded)		0.114				19.4 (MTO) 23.7 (Moulded)				
	+0.25 to +6.00 (0.25 steps)																	

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]





‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

§ Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Proclear® XR toric	-10.00 to -7.00 (0.50 steps)	-0.75 to -5.75D (0.50D steps)	5 to 180 (5 steps)	— —	Toric	— —	Daily wear; 30 days replacement	8.4	14.4	0.212	PC Technology® (phosphoryl choline)	omafilcon B	62	10.4	0.4	No	Yes	2
	-6.50 to Plano (0.25 steps)							+0.25 to +6.50 (0.25 steps)		8.8				0.159				
 Proclear® multifocal	-8.00 to -7.00 (0.50 steps)	— —	— —	+1.00 +1.50 +2.00 +2.50	Multifocal D lens N lens	— —	Daily wear; 30 days replacement	8.7	14.4	0.157 to 0.161 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	14 (MTO)	0.4	No	Yes	2
	-6.50 to Plano (0.25 steps)							+0.25 to +6.00 (0.25 steps)		8.4				0.060 to 0.113 (add dependant)				
 Proclear® XR multifocal	-20.00 to -7.00 (0.50 steps)	— —	— —	+1.00 to +4.00 (0.50 steps)	Toric Multifocal D lens N lens	— —	Daily wear; 30 days replacement	8.4	14.4	0.060 to 0.113 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	From: 14.0 (-3.00D/ +4.00D, N Type) To: 16.7 (-3.00D/ +2.50D, D type)	0.4	No	Yes	2
	-6.50 to Plano (0.25 steps)							+0.25 to +6.50 (0.25 steps)										
 Proclear® multifocal toric	-20.00 to -7.00 (0.50 steps)	-0.75 to -5.75 (0.50 steps)	5 to 180 (5 steps)	+1.00 to +4.00 (0.50 steps)	Toric Multifocal D lens N lens	— —	Daily wear; 30 days replacement	8.4	14.4	0.060 to 0.115 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	From: 14.5 (-3.00D/ +4.00D, N Type) To: 17.7 (-3.00D/ +4.00D, D Type)	0.4	No	Yes	2
	-6.50 to Plano (0.25 steps)							+0.25 to +6.50 (0.25 steps)										

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]


‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

§ Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
www.coopervision.nl



Product	Sphere Power (DS)*	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t†	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class ‡	Visibility Tint	FDA Group
 Biomedics® 55 Evolution [Biomedics 55 UV Asphere]	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	---	---	---	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement	8.6, 8.8, 8.9	14.2	0.075	---	ocufilcon D	55	26	0.4	69% UVA & 97% UVB; Class 2	Yes	4
 Biomedics® toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	---	Toric	---	Daily wear; 30 days replacement	8.7	14.5	0.109	---	ocufilcon D	55	18	0.4	69% UVA & 97% UVB; Class 2	Yes	4

* Plano lens availability for sphere product can vary by market or customer.

† (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂) / (ml x mmHg)]

‡ UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.